

1 (March 13, 1995)
2 Rollers shall be self-powered pneumatic tired rollers with a ground contact pressure
3 of approximately 276 kPa, or steel wheel two- or three-axle tandem, or three-wheel
4 rollers, with a mass not less than 8 tonnes, or any combination of the above.
5 Vibratory rollers shall not be allowed.
6
7 After placement, the bituminous mixture shall be compacted to the thickness shown
8 in the Plans.